



ZHEJIANG GANGLONG NEW MATERIAL CO., LTD.

MAQIAO WARP KNITTING SCIENCE & TECHNOLOGY INDUSTRIAL ZONE

HAINING ZHEJIANG CHINA, 314419

TECHNICAL DATA GLP014

COATED BLOCKOUT 610G (M)

Item	Unit	Value		Test Method
Base Fabric	Denier	500DX500D		(High tenacity yarn) 100%PES
Construction	Weaving/inch	28X28		/
Weight of fabric	Gsm/m2	122±10		DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	488±10		DIN53352 BS3424 Method5B
Total weight	Gsm/m2	610±20		DIN53352 BS3424 Method5A
Thickness	mm	0.48±0.02		DIN EN ISO 2286-3
Width	cm	Up to 500		/
Tensile Strength	N/5cm	Warp	1850	DIN53352 BS3424
		Weft	1550	
Tearing Strength	N	Warp	235	DIN53356 BS3424
		Weft	220	
Adhesion	N/5CM	80		DIN53357 BS3425 Method9B
Temperature Resistance	℃	－20～70		DIN53357 BS3425 Method10
Lacquering	None			
Flammability	B1			
LOW CADMIUM & HEAVY METALS	Reach Compliance			
Conclusions and Announcements	Declaration by GLP: Please choose GLP products suitably according to relative provisions or industrial standards. GLP bears the responsibility for the specified technical and performance data on this page only. GLP is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)			
	Remarks : “M” represents Matte surface			